

ASIIC UK LTD



Product catalogue





ILMENITE CONCENTRATE GRADE "K"

Specification TUU:13.2- 31614145-
001:2008

ILMENITE CONCENTRATE Grade K	TiO ₂	Al ₂ O ₃	SiO ₂	H ₂ O
Standard	63,00	3,00	2,00	0,50
Typical	64,00	1,90	1,35	0,40



ILMENITE CONCENTRATE
ІЛЬМЕНІТОВИЙ КОНЦЕНТРАТ



RUTILE CONCENTRATE GRADE “KP”

Specification *TUU:07.2-30454644-001:2019*

RUTILE CONCENTRATE Grade KP	TiO ₂	Fe ₂ O ₃	Al ₂ O ₃	SiO ₂	ZrO ₂	P ₂ O ₅	SO ₃	H ₂ O
Standard	94,00	2,80	0,60	1,50	1,00	0,07	0,05	0,50
Typical	95,50	1,40	0,40	0,90	0,65	0,05	0,03	0,10





ZIRCON CONCENTRATE GRADE “GZK”

Specification TUU:07.2- 30454644-002:2019

ZIRCON CONCENTRATE Grade GZK	ZrO ₂ +HfO	Al ₂ O ₃	Fe ₂ O ₃	TiO ₂	H ₂ O
Standard	65,00	2,10	0,10	0,40	0,50
Typical	65,50	1,50	0,07	0,25	0,10




ZIRCON CONCENTRATE
ЦИРКОНОВИЙ КОНЦЕНТРАТ



KYANITE-SILLIMANITE CONCENTRATE GRADE “GKSC”

Specification TUU:07.2- 30454644-003:2019

KYANITE-SILLIMANITE CONCENTRATE Grade GKSC	Al ₂ O ₃	TiO ₂	Fe ₂ O ₃	CaO	MgO	H ₂ O
Standard	57,00	2,00	0,80	0,20	0,40	0,50
Typical	57,70	0,95	0,75	0,10	0,25	0,10





STAUROLITE CONCENTRATE

Specification TU U: 07.2-30454644-004:2019

STAUROLITE CONCENTRATE	Al ₂ O ₃ +TiO ₂	SiO ₂	H ₂ O
Standard	45,50	29,00	0,50
Typical	46,50	27,00	0,40

